

80 to 73 nearly; for as 80 to 73, so is 480 to 438; and lastly, that the *Avoirdupois* Pound and Ounce is to the *Paris* Two *Marc* Weight and Ounce, as 63 to 68 nearly; for as 63 to 68, so is 7004 to 7559.873.

4. The *Paris* Foot, expressed in Decimals, is equal to 1.0654 of the *English* Foot, or contains 12.785 *English* Inches.

---

VI. *A Method of making a Gold-colour'd Glazing for Earthen-Ware; communicated, in Latin, in a Letter from M. Godofridus Heinſius, Aſtron. Prof. at St. Petersburg, to Mr. Peter Collinſon, F. R. S.*

Read Nov. 11.  
1742.

**T**AKE of Litharge parts iij. of Sand or calcined Flint p. i. pound and mix these very well together, then run them into a yellow Glass with a strong Fire. Pound this Glass, and grind it into a subtile Powder, which moisten with a well saturated Solution of Silver, make it into a Paste, which put into a Crucible, and cover it with a Cover. Give at first a gentle Degree of Fire, then increase it, and continue it till you have a Glass, which will be green. Pound this Glass again, and grind it to a fine Powder; moisten this Powder with some Beer, so that by means of an Hair Pencil you may apply it upon the Vessels, [or any Piece of Earthen-ware]. The Vessels that are painted or cover'd over with this Glazing, must be first well heated, then put under a Muffle, and as soon as the Glass runs, you must \* smook them, and take out the Vessels.

---

\* *Afflare, debes fumum.*